

Supercored 71H

FLUX CORED ARC WELDING CONSUMABLES
FOR WELDING OF Mild & 490Mpa CLASS
HIGH TENSILE STEEL

2024.12

HYUNDAI WELDING CO., LTD.



❖ Specification

AWS A5.20 E71T-1C,-9C-J

(AWS A5.20M) E491T-1C,-9C-J

EN ISO 17632-A T42 4 P C1 1

JIS Z3313 T49 4 T1-1 C A

AWS D1.8

Wire Dia. mm(in)		
1.2(0.045)	1.4(0.052)	1.6(1/16)

* AWS D1.8 is available upon request

❖ Applications

All position welding of shipbuilding, bridge, building and structural fabrications.

❖ Characteristics on Usage

Supercored 71H is a titania flux cored wire for all position welding with high amperage.

Its impact value is very good under high heat input, arc is smooth and slag detachability is excellent.

❖ Note on Usage


1. For preheating guidelines, please refer to your local standards and codes relative to your best practices.
2. One-side welding defect such as hot cracking may occur with welding parameter such as high welding speed.
3. Use 100% CO₂ gas.



Typical Mechanical Properties & Chemical Composition of All Weld Metal

❖ Welding Conditions

Method by AWS Spec.



[Joint Preparation & Layer Details]

Welding Position	: 1G(PA)
Diameter	: 1.2mm (0.045in)
Shielding Gas	: 100%CO ₂
Flow Rate	: 20 ℓ /min
Amp./ Volt.	: 280A / 32V
Stick-Out	: 20~25mm (0.79~0.98in)
Pre-Heat	: R.T .
Interpass Temp.	: 150±15℃ (302±59°F)
Polarity	: DC(+)

❖ Mechanical Properties of all weld metal

Consumable	Tensile Test			CVN Impact Test J(ft · lbs)	
	YS MPa (lbs/in ²)	TS MPa (lbs/in ²)	EL (%)	-29℃ (-20°F)	-40℃ (-40°F)
Supercored 71H	550 (80,000)	570 (83,000)	28.0	90 (66)	60 (44)
AWS A5.20 E71T-1C,-9C-J	≥ 390 (56,000)	490~670 (70,000~ 97,000)	≥ 22	≥ 27J at -40℃ (≥ 20ft · lbs at -40°F)	

❖ Chemical Analysis of all weld metal(wt%)

Consumable	C	Si	Mn	P	S
Supercored 71H	0.03	0.46	1.36	0.008	0.011
AWS A5.20 E71T-1C,-9C-J	≤ 0.12	≤ 0.9	≤ 1.75	≤ 0.03	≤ 0.03


This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.



Typical Mechanical Properties & Chemical Composition of All Weld Metal

❖ Welding Conditions

Method by AWS Spec.



[Joint Preparation & Layer Details]

Welding Position	: 1G(PA)
Diameter	: 1.4mm (0.052in)
Shielding Gas	: 100%CO ₂
Flow Rate	: 20 ℓ /min
Amp./ Volt.	: 300A / 32V
Stick-Out	: 20~25mm (0.79~0.98in)
Pre-Heat	: R.T .
Interpass Temp.	: 150±15℃ (302±59°F)
Polarity	: DC(+)

❖ Mechanical Properties of all weld metal

Consumable	Tensile Test			CVN Impact Test J(ft · lbs)	
	YS MPa (lbs/in ²)	TS MPa (lbs/in ²)	EL (%)	-29℃ (-20°F)	-40℃ (-40°F)
Supercored 71H	560 (81,000)	580 (84,000)	27.5	85 (63)	60 (44)
AWS A5.20 E71T-1C,-9C-J	≥ 390 (56,000)	490~670 (70,000~ 97,000)	≥ 22	≥ 27J at -40℃ (≥ 20ft · lbs at -40°F)	

❖ Chemical Analysis of all weld metal(wt%)

Consumable	C	Si	Mn	P	S
Supercored 71H	0.04	0.45	1.35	0.009	0.012
AWS A5.20 E71T-1C,-9C-J	≤ 0.12	≤ 0.9	≤ 1.75	≤ 0.03	≤ 0.03


This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.



Typical Mechanical Properties & Chemical Composition of All Weld Metal

❖ Welding Conditions

Method by AWS Spec.



[Joint Preparation & Layer Details]

Welding Position	: 1G(PA)
Diameter	: 1.6mm (1/16in)
Shielding Gas	: 100%CO ₂
Flow Rate	: 20 ℓ /min
Amp./ Volt.	: 320~330A / 29~30V
Stick-Out	: 20~25mm (0.79~0.98in)
Pre-Heat	: R.T .
Interpass Temp.	: 150±15℃ (302±59°F)
Polarity	: DC(+)

❖ Mechanical Properties of all weld metal

Consumable	Tensile Test			CVN Impact Test J(ft · lbs)	
	YS MPa (lbs/in ²)	TS MPa (lbs/in ²)	EL (%)	-29℃ (-20°F)	-40℃ (-40°F)
Supercored 71H	550 (80,000)	570 (83,000)	27.5	85 (63)	55 (41)
AWS A5.20 E71T-1C,-9C-J	≥ 390 (56,000)	490~670 (70,000~ 97,000)	≥ 22	≥ 27J at -40℃ (≥ 20ft · lbs at -40°F)	

❖ Chemical Analysis of all weld metal(wt%)

Consumable	C	Si	Mn	P	S
Supercored 71H	0.04	0.45	1.34	0.009	0.011
AWS A5.20 E71T-1C,-9C-J	≤ 0.12	≤ 0.9	≤ 1.75	≤ 0.03	≤ 0.03

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.



Welding Efficiency

❖ Deposition Rate & Efficiency

Consumable (size)	Welding Conditions		Wire Feed Speed m/min (in/min)	Deposition Efficiency %	Deposition Rate kg/hr(lb/hr)
	Amp.(A)	Volt.(V)			
Supercored 71H 1.2mm (0.045in)	200	26	10.2 (400)	84~87	3.4 (7.5)
	250	28	11.5 (450)	85~88	4.5 (9.9)
	300	33	15.3 (600)	86~88	5.2 (11.4)
Supercored 71H 1.4mm (0.052in)	250	28	7.6 (300)	85~87	3.9 (8.6)
	300	32	10.2 (400)	85~88	4.8 (10.6)
	330	36	12.8 (500)	86~89	5.8 (12.8)
Supercored 71H 1.6mm (1/16in)	280	31	6.4 (250)	85~88	4.2 (9.2)
	330	33	7.6 (300)	86~88	4.8 (10.6)
	350	34	8.1 (320)	87~89	5.3 (11.7)
	400	38	9.2 (360)	87~90	5.7 (12.5)
Remark				Deposition efficiency =(Deposited metal weight/ Wire weight used)×100	Deposition rate =(Deposited metal weight/ Welding time,min.)×60

* Shielding Gas : 100%CO₂

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.



Diffusible Hydrogen Content

❖ Welding Conditions

Diameter	: 1.4mm(0.052in)	Amps(A) / Volts(V)	: 230A / 24V
Shielding Gas	: 100%CO ₂	Stick-Out(mm)	: 20~25mm (0.79~0.98in)
Flow Rate	: 20 ℓ /min	Welding Speed	: 30 cm/min (12 in/min)
Welding Position	: 1G (PA)	Current Type & Polarity	: DC(+)

❖ Hydrogen Analysis Using Gas Chromatograph Method

Hydrogen Evolution Time	: 72 hrs
Evolution Temp.	: 45 °C (113°F)
Barometric Pressure	: 780 mm-Hg

❖ Result(ml/100g Weld Metal)

X1	X2	X3	X4
4.0	4.1	4.1	4.2

Average Hydrogen Content 4.1 ml / 100g Weld Metal



Proper Welding Condition

❖ Proper Current Range

Consumable	Shielding Gas	Welding Position	Wire Dia.		
			1.2mm (0.045in)	1.4mm (0.052in)	1.6mm (1/16in)
Supercored 71H	100%CO ₂	F & HF	110~280Amp	110~280Amp	120~300Amp
		V-Up & OH	110~240Amp	110~260Amp	120~280mp
		V-Down	110~280Amp	110~280Amp	120~300Amp

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.



Approvals

❖ Shipping Approvals

Welding Position	Register of shipping & Size					
	KR	ABS	LR	BV	DNV	NK
All V-Down	4YSMG(C) H10 1.2~1.4mm (0.045~ 0.052in)	4YSAH10 1.2~1.4mm (0.045~ 0.052in)	4YSH10 1.2~1.4mm (0.045~ 0.052in)	SA4YM HH 1.2~1.4mm (0.045~ 0.052in)	IVYSM(H5) 1.2~1.4mm (0.045~ 0.052in)	KSW54G(C) H10 1.2~1.4mm (0.045~ 0.052in)
	3YSMG(C) H10 1.6mm (1/16in)	3SAH10 1.6mm (1/16in)		SA3YM HH 1.6mm (1/16in)	IIYMS(H5) 1.6mm (1/16in)	KSW53G(C) H10 1.6mm (1/16in)

❖ F No & A No

F No	A No
6	1